



**SHIDIMO**  
INTERAUX PVT. LTD.



*Quality.... An Obsession With us*

**Manufacturer of :**

*Acid dyes, Acid milling dyes, Metal complex dyes,  
Direct dyes, Mordant dyes*



**SHIDIMO**  
INTERAUX PVT. LTD.

**DYEING ON NYLON, WOOL & SILK**

Nylon 2%	Wool 3%	Silk 2%	Product Name
			<b>Shidomill Yellow 2G</b> *Acid Yellow 17
			<b>Shidocid Yellow GP</b> *Acid Yellow 19
			<b>Shidocid Yellow N6G</b>
			<b>Shidomill Yellow MY</b> *Acid Yellow 42
			<b>Shidocid Yellow N5GN</b>
			<b>Shidolan Yellow GR</b> *Acid Yellow 99
			<b>Shidomill Yellow 5GN</b> Acid Yellow 110
			<b>Shidolan Yellow A3RL</b> *Acid Yellow 194
			<b>Shidolan Yellow GL</b> *Acid Yellow 237
			<b>Shidolan Yellow A2GLN</b> *Acid Yellow 241

The information given is accurate to the best of our knowledge without obligation



# SHIDIMO

INTERAUX PVT. LTD.

## DYEING ON NYLON, WOOL & SILK

Nylon 2%	Wool 3%	Silk 2%	Product Name
			<b>Shidocid Yellow 8G</b> *Acid Yellow 250
			<b>Shidocid Brown 2G</b> *Acid Orange 24
			<b>Shidolan Orange G</b> *Acid Orange 74
			<b>Shidolan Orange ARL</b> *Acid Orange 142
			<b>Shidomill Rhodamine G</b> *Acid Red 50
			<b>Shidomill Rhodamine B</b> *Acid Red 52
			<b>Shidomill Red NG</b>
			<b>Shidomill Fast Red A</b> *Acid Red 88
			<b>Shidomill Scarlet G</b> *Acid Red 97
			<b>Shidomill Red KRS</b>



# SHIDIMO

INTERAUX PVT. LTD.

## DYEING ON NYLON, WOOL & SILK

Nylon 2%	Wool 3%	Silk 2%	Product Name
			<b>Shidomill Maroon V</b> *Acid Red 119
			<b>Shidomill Red 3BN</b> *Acid Red 131
			<b>Shidomill Red F2R</b> *Acid Red 151
			<b>Shidolan Pink BE</b> *Acid Red 186
			<b>Shidolan Red BG</b> *Acid Red 198
			<b>Shidomill Red B</b> *Acid Red 249
			<b>Shidocid Red C</b> *Acid Red 449
			<b>Shidomill Crimson</b>
			<b>Shidomill Violet 5B</b> *Acid Violet 17
			<b>Shidomill Red 10B</b> *Acid Violet 54

The information given is accurate to the best of our knowledge without obligation



# SHIDIMO

INTERAUX PVT. LTD.

## DYEING ON NYLON, WOOL & SILK

Nylon 2%	Wool 3%	Silk 2%	Product Name
			<b>Shidolan Bordeaux MB</b> *Acid Violet 90
			<b>Shidocid Patent Blue AS</b> *Acid Blue 7
			<b>Shidocid Blue FF</b> *Acid Blue 15
			<b>Shidomill Blue BM</b> *Acid Blue 29
			<b>Shidomill Fast Blue R</b> *Acid Blue 92
			<b>Shidomill Blue S5R</b> *Acid Blue 113
			<b>Shidolan Blue 2G</b> *Acid Blue 158
			<b>Shidolan Blue MTR</b> *Acid Blue 193
			<b>Shidocid Blue C</b> *Acid Blue 359
			<b>Shidomill Turquoise Blue AS</b>

The information given is accurate to the best of our knowledge without obligation



# SHIDIMO

INTERAUX PVT. LTD.

## DYEING ON NYLON, WOOL & SILK

Nylon 2%	Wool 2%	Silk 2%	Product Name
			Shidomill Silk Blue BR
			Shidocid Green V *Acid Green 16
			Shidolan Olive BGL *Acid Green 104
			Shidomill Green LP
			Shidomill Resorcine Brown R *Acid Brown 14
			Shidolan Brown CER *Acid Brown 75
			Shidolan Brown ABL *Acid Brown 355
			Shidolan Brown A2RL *Acid Brown 365
			Shidomill Brown HGIN
			Shidomill Brown IEB

The information given is accurate to the best of our knowledge without obligation



# SHIDIMO

INTERAUX PVT. LTD.

## DYEING ON NYLON, WOOL & SILK

Nylon 2%	Wool 3%	Silk 2%	Product Name
			<b>Shidomill Brown BFI</b>
			<b>Shidomill Brown BRI</b>
			<b>Shidomill Fast Black B</b> *Acid Black 24
			<b>Shidolan Black MSRL</b> *Acid Black 194
			<b>Shidomill Black NG</b> *Acid Black 210
			<b>Shidomill Black FG</b> *Acid Black 234
			<b>Shidonyl Orange TGLL</b> *Direct Orange 34
			<b>Shidonyl Red B</b> *Direct Red 81

The information given is accurate to the best of our knowledge without obligation



# SHIDIMO

INTERAUX PVT. LTD.

## DYEING ON NYLON, WOOL & SILK

Nylon 2%	Wool 3%	Silk 2%	Product Name
			<b>Shidomill Brown BFI</b>
			<b>Shidomill Brown BRI</b>
			<b>Shidomill Fast Black B</b> *Acid Black 24
			<b>Shidolan Black MSRL</b> *Acid Black 194
			<b>Shidomill Black NG</b> *Acid Black 210
			<b>Shidomill Black FG</b> *Acid Black 234
			<b>Shidonyl Orange TGLL</b> *Direct Orange 34
			<b>Shidonyl Red B</b> *Direct Red 81





**SHIDIMO**  
INTERAUX PVT. LTD.

**DYEING ON NYLON, WOOL & SILK**

Sr. No	Product Name	C.I. No.	Solubility gpl@ 90°C	Fastness		
				Light	Washing	Perspiration
21.	Shidomill Maroon V	Acid Red 119	60	5	5	5
22.	Shidomill Red 3BN	Acid Red 131	50	4	5	4-5
23.	Shidomill Red F2R	Acid Red 151	30	4	5	5
24.	Shidolan Pink BE	Acid Red 186	40	5-6	4	4
25.	Shidolan Red BG	Acid Red 198	40	6-7	4-5	3-4
26.	Shidomill Red B	Acid Red 249	40	5	2	4
27.	Shidocid Red C	Acid Red 449	20	4	3	3
28.	Shidomill Crimson		50	4	4	3
29.	Shidomill Violet 5B	Acid Violet 17	60	1	3	4
30.	Shidomill Red 10B	Acid Violet 54	50	5	5	4-5
31.	Shidolan Bordeaux MB	Acid Violet 90	30	6	4-5	4-5
32.	Shidocid Patent Blue AS	Acid Blue 7	80	2	4	4
33.	Shidocid Blue FF	Acid Blue 15	40	1	3-4	4-5
34.	Shidomill Blue BM	Acid Blue 29	60	7-8	2	1
35.	Shidomill Fast Blue R	Acid Blue 92	50	5	1	2
36.	Shidomill Blue S5R	Acid Blue 113	60	5	4	4
37.	Shidolan Blue 2G	Acid Blue 158	80	5	5	4
38.	Shidolan Blue MTR	Acid Blue 193	40	6-7	4-5	4-5
39.	Shidocid Blue C	Acid Blue 359	20	4	3	3
40.	Shidomill Turquoise Blue AS		60	2	4	4

The information given is accurate to the best of our knowledge without obligation



**SHIDIMO**  
INTERAUX PVT. LTD.

**DYEING ON NYLON, WOOL & SILK**

Sr. No	Product Name	C.I. No.	Solubility gpl@90°C	Fastness		
				Light	Washing	Perspiration
41.	Shidomill Silk Blue BR		70	2	3	3
42.	Shidocid Green V	Acid Green 16	40	3	3	4-5
43.	Shidolan Olive BGL	Acid Green 104	40	6	4-5	4-5
44.	Shidomill Green LP		80	3	4	4
45.	Shidomill Resorcine Brown R	Acid Brown 14	70	4	4-5	4
46.	Shidolan Brown CER	Acid Brown 75	40	4	3-4	3-4
47.	Shidolan Brown ABL	Acid Brown 355	50	6-7	4-5	4-5
48.	Shidolan Brown A2RL	Acid Brown 365	60	6	4-5	4-5
49.	Shidomill Brown HGIN		60	5	5	5
50.	Shidomill Brown IEB		60	5	5	5
51.	Shidomill Brown BFI		60	5	5	5
52.	Shidomill Brown BRI		60	5	5	5
53.	Shidomill Fast Black B	Acid Black 24	50	6	3-4	4-5
54.	Shidolan Black MSRL	Acid Black 194	70	6	6	6
55.	Shidomill Black NG	Acid Black 210	60	6	3	3
56.	Shidomill Black FG	Acid Black 234	60	4	3	4
57.	Shidonyl Orange TGLL	Direct Orange 34	40	6	3	3
58.	Shidonyl Red B	Direct Red 81	40	6	5	5

The information given is accurate to the best of our knowledge without obligation